

CONCRETE DECKING

TECHNICAL BULLETIN CTB-23

Rev 4, February 2004

This issue supersedes all previous issues

The use of galvanised products for the formation of profiled concrete formwork decking which is permanently placed prior to pouring the reinforced concrete slab has been a common building practice within Australia for over 20 years. Galvanized material is well suited to applications involving contact with concrete slurries and the mild etching that the highly alkaline mix initiates. This leads to superior bonding with the galvanized deck.

However, there are four areas that are of direct concern with regard to possible corrosion. These are:

Firstly, corrosion can result from poor detailing and positioning of the concrete reinforcing components, the positioning of the structural reinforcing steel or the positioning of expansion joints. The poor performance of any of these components will lead to the penetration of water through exposed concrete decks causing premature failure of the supporting galvanized structural deck and any associated structural steelwork.

Secondly, corrosion of the bottom surface of the deck is also possible where the decking either constitutes a severely unwashed area, is placed in a severe environment or is placed at distances closer than 450 mm to moist soil.

Characteristic unwashed area corrosion mechanisms, will lead to the early consumption of the metallic coating in severe marine and other severe environments. Heavy coating mass galvanized material should be considered for use in such environments and further post painting of the decking with a high build industrial coating system may be required.

Thirdly, incorrect edge detailing will lead to the direction of run off waters from the slab surface into the shrinkage gap between the edge of the supported concrete slab and the structural steel decking. This will lead to corrosion of the galvanized component of the decking at the interface and possibly, the loss of structural requirements.

Finally, in all cases where studs are to be welded to structural steel beam, the surface in contact with the steel decking should be coated with a weld-through primer of an appropriate thickness (25 μ). This is to prevent dissimilar metal corrosion of the galvanized steel decking. Given the difficulty of rectification, subsequent to installation, it is strongly recommended that this practice be followed.

Figure 1: Corroded concrete decking showing the result of sub-standard expansion joint and finish detail.



ZINCALUME® zinc/aluminium alloy-coated steel is not recommended for concrete decking as formwork. While ZINCALUME® steel is resistant to corrosion in most atmospheric environments it is rapidly attacked by the alkaline concrete mix and must not be selected for this end use.

The information and advice contained in this Bulletin is of a general nature only, and has not been prepared with your specific needs in mind. You should always obtain specialist advice to ensure that the materials, approach and techniques referred to in this Bulletin meet your specific requirements.

BlueScope Steel Limited makes no warranty as to the accuracy, completeness or reliability of any estimates, opinions or other information contained in this Bulletin, and to the maximum extent permitted by law, BlueScope Steel Limited disclaims all liability and responsibility for any loss or damage, direct or indirect, which may be suffered by any person acting in reliance on anything contained in or omitted from this document.

ZINCALUME® is a registered trade mark of BlueScope Steel Limited.

BlueScope is a trade mark of BlueScope Steel Limited.

Please ensure you have the current Technical Bulletin as displayed at www.bluescopesteel.com.au

BlueScope Steel

Copyright© 2003 BlueScope Steel Limited

BlueScope Steel Limited ABN 16 000 011 058

BlueScope Steel (AIS) Pty Ltd ABN 19 000 019 625



AUSTRALIA

SYDNEY	Telephone: (02) 9795 6700
MELBOURNE	Telephone: (03) 9586 2222
BRISBANE	Telephone: (07) 3845 9300
ADELAIDE	Telephone: (08) 8243 7333
PERTH	Telephone: (08) 9330 0666

OVERSEAS

BlueScope Steel (Malaysia) Sdn Bhd	Telephone: (603) 3250 8333
BlueScope Steel (Thailand) Limited	Telephone: (66 38) 685 710
PT BlueScope Steel Indonesia	Telephone: (62 21) 570 7564
BlueScope Steel Southern Africa (Pty) Limited	Telephone: (27 21) 555 4265

Produced by Artimprint (02) 9984 8586

