

CORROSION

FERTILIZER MANUFACTURING AND STORAGE BUILDINGS

TECHNICAL BULLETIN CTB-24

Rev 3, November 2003

This issue supersedes all previous issues

The manufacture of fertilizers utilises high concentrations of phosphorous, sulphur and chloride containing compounds along with other corrosive contaminants. Storage of the final fertilizer product in open piles, ie not in sealed bags, will also release these contaminants into the environment. The presence of these contaminants in the surrounding environment of a building will accelerate the corrosion of ZINCALUME® zinc/aluminium alloy coated steel, COLORBOND® prepainted steel and COLORBOND® Ultra prepainted steel.



Figure 1: Example of corrosion resulting from contact with fertilizer.

The broad spectrum of fertilizer products manufactured to meet the demands of the agriculture industry may expose the cladding material to a variety of fertilizer products during the service life of the building. Therefore, COLORBOND® Stainless prepainted steel is the only product recommended by BlueScope Steel Limited for roof and wall sheeting on fertilizer manufacturing and storage buildings.

As purlins are exposed to the same environment, BlueScope Steel recommend they be manufactured from GALVSPAN® Z450 steel and incorporate a turned-down lip to prevent the build-up of fertilizer dust. Furthermore, the purlins must be postpainted with an appropriate high-build industrial paint system as



Figure 2: Build-up on purlin

Design

Experience has shown that the incorporation of a masonry dwarf wall can dramatically reduce the instance of mechanical damage and corrosion to wall cladding. This avoids direct contact between the fertilizer and the cladding.

In cases where end lapping of roof sheeting is required, particular care should be taken to encapsulate the top end of the lapped sheet, using a generous bead of neutral cure silicon rubber sealant, to prevent the retention of fertilizer dust (*refer CTB-8*).



Figure 3: Example of a dwarf wall

Should products other than COLORBOND® Stainless steel be used as cladding, the following problems may be encountered:

- accelerated corrosion under flashings, ridge cappings and at the roof/purlin interface, where fertilizer dust is allowed to build up
- reduced service life

The information and advice contained in this Bulletin is of a general nature only, and has not been prepared with your specific needs in mind. You should always obtain specialist advice to ensure that the materials, approach and techniques referred to in this Bulletin meet your specific requirements.

BlueScope Steel Limited makes no warranty as to the accuracy, completeness or reliability of any estimates, opinions or other information contained in this Bulletin, and to the maximum extent permitted by law, BlueScope Steel Limited disclaims all liability and responsibility for any loss or damage, direct or indirect, which may be suffered by any person acting in reliance on anything contained in or omitted from this document.

COLORBOND® and ZINCALUME® are registered trade marks of BlueScope Steel Limited.

BlueScope is a trade mark of BlueScope Steel Limited.

Please ensure you have the current Technical Bulletin as displayed at www.bluescopesteel.com.au

BlueScope Steel

Copyright© 2003 BlueScope Steel Limited

BlueScope Steel Limited ABN 16 000 011 058

BlueScope Steel (AIS) Pty Ltd ABN 19 000 019 625



AUSTRALIA	SYDNEY	Telephone: (02) 9795 6700
	MELBOURNE	Telephone: (03) 9586 2222
	BRISBANE	Telephone: (07) 3845 9300
	ADRIANUM	Telephone: (09) 8243 7133

OVERSEAS	BlueScope Steel (Malaysia) Sdn Bhd	Telephone: (603) 3250 8333
	BlueScope Steel (Thailand) Limited	Telephone: (66 38) 685 710
	PT BlueScope Steel Indonesia	Telephone: (62 21) 570 7564

